

CERTAL®

Alloy's Characteristics	
Alloy	EN AW 7022 (special type)
Type of Alloy	heat treatable
Temper	T651
Surface	rolled skin

Mechanical Properties ¹⁾		Typical values
Yield strength R _{p0,2}	[MPa]	400 – 495
Ultimate tensile strength R _m	[MPa]	490 – 555
Elongation A ₅₀	[%]	6 – 9
Hardness HBW	[2,5/62,5]	165 – 170

Physical Properties ¹⁾		Typical values
Density	[g/cm ³]	2.76
Module of elasticity	[GPa]	72
Electrical conductivity	[m/Ω · mm ²]	18 – 22
Coefficient of thermal expansion	[K ⁻¹ · 10 ⁻⁶]	23.6
Thermal conductivity	[W/m · K]	120 – 150
Specific heat capacity	[J/kg · K]	862

Processing Characteristics ²⁾		Typical values
Dimensional stability		2 – 3
Machinability		1
Erodability		1
Weldability (Gas / TIG / MIG / Resistance / EB)		6 / 6 / 6 / 2 / 3
Corrosion resistance (seawater / weather/ stress cracking)		5 / 5 / 4
Use at temperatures (max °C long/short terms) ³⁾		90 / 120
Anodising (technical / decorative / hard-) ⁴⁾		3 / 6 / 2
Polishability		1
Etching		1 – 2
Contact with food (according to EN 602)		no

Tolerances			
Thickness in [mm]	Flatness [mm] ⁵⁾	Thickness [mm]	Width & Length [mm]
< 150	DIN EN 485-3	DIN EN 485-3	-0/+20 & -0/+10
Zuschnitte			DIN ISO 2768-1m

Standard Stock Sizes		
Plate Dimension [mm]	1.520 × 3.020	in thickness of 8 – 100 mm
	1.400 × 3.020	in thickness of 110 mm
	1.200 × 3.020	in thickness of 120 mm
	1020 × 3020	in thickness of 130 mm
	950 × 3.020	in thickness of 140 mm
Plate Thickness [mm]	8, 10, 12, 15, 20, 25, 30, 35, 40, 45, 50	
	60, 70, 80, 90, 100, 110, 120, 130, 140	
Other dimension upon request		

Date: 12.07.2016

- 1) Typical values at room temperature.
- 2) Ratings evaluation rating from 1 (very good) to 6 (inapplicable).
- 3) Without loss of strength after cooling down.
- 4) Technical anodising only - no warranty towards optical demands.
- 5) Surface flatness for whole plates is measured with a special, 1 meter long, digital flatness ruler.

CERTAL® is a registered trademark of CONSTELLIUM Valais SA